

# GC ULTRA-BOND 80 SC

## EPOXY-WATER BASED PRIMER, LOW VOC VERSION

**GC ULTRA-BOND 80 SC** is a two component, liquid applied, epoxy-polyamine primer with enhanced bonding characteristics as an intercoat\*. GC Ultra-Bond 80 SC is designed to be in compliance with SCQAMD air quality standards.

GC Ultra-Bond 80 SC has excellent adhesion, low viscosity, as a penetrating concrete sealing primer.

### RECOMMENDED USES

- Concrete
- Ferrous Metal
- Plywood
- Polyurethane Coating\*

### PACKAGING

2-gallon kit: Side-A at 1 gallon and Side-B at 1 gallon

10-gallon kit: Side-A at 5 gallons and Side-B at 5 gallons

### COLOR

Side-A: Black

Side-B: White

### TECHNICAL DATA

PHYSICAL PROPERTIES	
Coverage	1 gal / 300 sqft
Dry Film Thickness (1 gal / 300 sqft)	4 ± 1 mils
Specific Gravity	Side-A: 1.30 Side-B: 1.89
Pot Life @ 75°F (24°C), 50% R.H.	60-90 minutes
Total Solids by Weight, ASTM D2369	90 ± 2%
Total Solids by Volume, ASTM D2697	84 ± 2%
Viscosity at 75°F (24°C), Part-A & Part-B Combined	1200 ± 200 cps
Volatile Organic Compound, ASTM D2369-81	100 g / L
Dry Time	3-5 hours
Topcoat Time	8-12 hours
Recoat Time	24-48 hours

### REQUIREMENTS

GC Ultra-Bond 80 SC is an epoxy primer which should be applied only by trained or manufacturer-approved roofing experts familiar with the properties of this material.

### EQUIPMENT

It can be applied using an airless sprayer, brush, or phenolic resin core roller.

## APPLICATION

This product contains Epoxy Resin and Curatives.

Surfaces must be dry, clean and free of foreign matter. Recommended surface temperature should be greater than 50°F (10°C) and at least 5°F (3°C) above the dew point.

GC Ultra-Bond 80 SC should be applied at the rate of 1 gallon (mixture of Side-A & Side-B) /300 sqft or 300 sqft/gallon. Coverage rate will depend on surface roughness, porosity or bleed block requirement.

Allow GC Ultra-Bond 80 SC to become tack free before applying the coating. Not UV stable.

GC Ultra-Bond 80 SC is very sensitive to heat and moisture. Higher temperatures and/or high humidity will significantly accelerate the cure time and pot life. Use caution in batch sizes and thickness of application. Low temperature and/or low humidity extend the cure time.

Containers that have been opened must be used as soon as possible. GC Ultra-Bond 80 SC is difficult to clean up after it has cured. Do not dilute GC Ultra-Bond 80 SC. Mix no more material than can be used within 45 minutes.

## MIXING

The volume mixing ratio is 1 part Side-A Black liquid to 1 part side-B White liquid. Do not mix in an up and down motion.

GC Ultra-Bond 80 SC Side-A and Side-B should be thoroughly mixed individually prior to combining to ensure a homogeneous material.

GC Ultra-Bond 80 SC must always be mixed with one part Side-A and one part Side-B (Side-A: Side-B = 1:1). The combined components should be thoroughly mixed using a mechanical mixer at slow speed.

## PROTECTIVE EQUIPMENT

Since GC Ultra-Bond 80 SC is atomized into a very fine particle distribution during spray application, it is essential that maximum effort is made to protect the spray mechanic and others near the workplace from undue exposure.

The best form of protection against organic solvents is the use of Type C organic vapor cartridge respirators. To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves. Wear safety glasses or OSHA-approved protective goggles.

## JOB-SITE PROTECTION

Overspray from GC Ultra-Bond 80 SC can carry considerable distances and attention should be given to the following:

1. Post warning signs a minimum of 100 feet from the work area.
2. Cover all intake vents near the work area.
3. Minimize or exclude all personnel not directly involved with the spray application.
4. No welding, smoking or open flames.
5. Have CO<sub>2</sub> or other dry chemical fire extinguisher

available at the jobsite.

6. Provide adequate ventilation.

## SHELF LIFE AND STORAGE

The shelf life of GC Ultra-Bond 80 SC is 12 months from the date of manufacture when stored in original unopened containers at temperatures between 50–75°F (10–24°C). Keep containers closed and store in a dry, cool place away from direct sunlight, heat, sparks, open flame, and moisture.

## FREIGHT CLASSIFICATION

Dangerous Goods. DOT regulations classify it as: UN 1263, PAINT, Class 3, PG III, FLAMMABLE LIQUID.

## HEALTH AND SAFETY

GCMC is committed to the health and safety of our customers. GCMC products shall only be installed by certified contractors. Applicators are required to follow all proper handling, safety and installation procedures. Safety Data Sheets (SDS) are available on this material. Any individual who may come in contact with these products should read and understand the SDS.

## VAPOR INHALATION

Respiratory protection is MANDATORY! The best form of protection against organic solvents or potentially sensitizing vapors in the workplace is a fresh air supply. Numerous manufacturers, including the 3M Company and MSA, make full face fresh air masks. For maximum protection, we recommend use of NIOSH/MSHA approved self-contained breathing apparatus with a full-face piece operated in a positive pressure mode. In well-ventilated application conditions, the use of Type C organic vapor cartridge respirators is acceptable. Effects of overexposure to vapor are characterized by nasal and respiratory irritation, dizziness, nausea, headache, fatigue, possible unconsciousness or even asphyxiation. Vapor inhalation problems are characterized by coughing, shortening of breath and tightness in the chest. Anyone exhibiting these types of symptoms should be immediately removed from the workplace and administered oxygen or fresh air. If the condition is prolonged or extreme, SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

## SKIN CONTACT

To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves. Skin contact with liquid components can result in a rash or other irritation. Wash the affected skin area with water. Wipe residual liquid from the skin with a clean cloth, then wipe the affected area with 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and water. If a rash or other irritation develops, see a physician.

## EYE CONTACT

Wear a full-face mask or OSHA-approved protective goggles. Eye Contact with liquid or sprayed components can result in corneal burns or abrasions. Upon exposure, eyes should be flushed with water for an extensive period.



## GC ULTRA-BOND 80 SC

### EPOXY-WATER BASED PRIMER, LOW VOC VERSION

SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

#### TECHNICAL SERVICES

Additional information, such as brochures, technical assistance, and management services are also available from a General Coatings Manufacturing Corp. Technical Consultant.

**LIMITED WARRANTY.** We warrant our Products to be free of manufacturing defects and to comply with the Product's current published physical properties when tested under controlled conditions. Our sole responsibility is limited to replacement of that portion of any Products found to be defective at the time of manufacture. There are no other warranties of any nature whatsoever, whether expressed or implied, including an express disclaimer of any warranty of merchantability or fitness for a particular purpose. Further, we disclaim any liability for damages of any type, however caused, including remote, consequential damages, or special damages resulting from any theory of liability, whether based on tort, negligence, or strict liability. We disclaim responsibility for any claims of intellectual property infringement through use of our Products in any manner. Where Products are used as a waterproofing membrane or floor coating, no warranty or guarantee is issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, abnormal wear and tear, or improper application by the applicator. Damage caused by abuse, neglect, lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded. In all instances and as a pre-condition to any available remedy, we reserve the right to conduct sample testing and performance analysis on any materials claimed to be defective, performed prior to any repairs being made by owner, general contractor, or applicator. Our limited warranty is void if repairs have been made or attempted, or if the claimed defect has been adulterated prior to our ability to conduct a formal investigative analysis.

**DISCLAIMER:** Please read all information in the general guidelines, technical data sheets, application guide and safety data sheets (SDS) before applying material. Products are for professional use only and should only be applied by professionals who have prior experience with our Products or have undergone specific training in their proper application. Published technical data and instructions are subject to change without notice. Contact your local representative or visit our website for current technical data and instructions. All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of these tests are not guaranteed and are not to be construed as a warranty, either expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with any product. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his own use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. We are not liable to the purchaser, end-user, or any third party for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, our Products. Recommendations or statements, whether verbal or in writing, shall not be binding upon us unless in writing and signed by one of our authorized corporate officers. Technical and application information is provided for establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and we make no claim that these tests or any other tests, accurately represent all environments. We are not responsible for typographical errors. © General Coatings Manufacturing Corporation. All Rights Reserved. Revision ULTRA BOND80SC\_08172020EA